

Z-CORE® Piping System

GENERAL SPECIFICATIONS

SECTION 1 – Scope

This section covers the use of fiberglass reinforced plastic (FRP) pipe for severe chemical process and chemical handling applications up to 275°F and 150 psig steady pressure.

The piping system shall be furnished and installed complete with all fittings, joining materials, supports, specials, and other necessary appurtenances.

SECTION 2 – General Conditions

2.01 Coordination. Material furnished and work performed under this section shall be coordinated with related work and equipment specified under other sections.

Valves	Section _____
Supports	Section _____
Equipment	Section _____

2.02 Governing Standards. Except as modified or supplemented herein, all materials and construction methods shall comply with the applicable provisions of the following specifications and be tested using the following standards:

Standard Specifications

ASTM D2997	Standard Specification for Centrifugal Cast "Fiberglass" (Glass-Fiber-Reinforced Thermosetting Resin) Pipe
------------	--

Standard Test Methods

ASTM D2992	Standard Practice for obtaining Hydrostatic or Pressure Design Basis for "Fiberglass" (Glass-Fiber-Reinforced Thermosetting Resin) Pipe
ASTM D1599	Standard Test Method for Short-Time Hydraulic Failure Pressure of Plastic Pipe, Tubing and Fittings
ASTM D2105	Standard Test Method for Longitudinal Tensile Properties of "Fiberglass" (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Tube
ASTM D2412	Standard Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading

ASTM D3567 Standard Practice for determining dimensions of "Fiberglass" (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Fittings

ASME B31.3 Process Piping

2.03 ASTM D2310 Designation Codes:
1"-8" RTRP-21CO

Mechanical properties cell classifications shown are minimum.

2.04 Operating Conditions. In addition to the above listed minimum design requirements, the system shall meet the following minimum operating conditions:

- Operating Pressure _____
- Operating Temperature _____
- Fluid Conveyed _____
- Test Pressure _____

2.05 Quality Assurance. Pipe manufacturer's quality program shall be in compliance with ISO 9001.

2.06 Delivery, Storage, and Handling. Pipe and fittings shall be protected from damage due to impact and point loading. Pipe shall be properly supported to avoid damage due to flexural strains. The contractor shall not allow dirt, debris, or other extraneous materials to get into pipe and fittings. All factory machined areas shall be protected from sunlight until installed.

2.07 Acceptable Manufacturers. FGS Smith Fibercast

SECTION 3 – Materials and Construction

3.01 1"-8" Pipe. The pipe shall be manufactured by the centrifugal casting process using the proprietary Z-resin, premium grade epoxy thermosetting resin to impregnate strands of continuous glass filaments. Pipe shall be heat cured and the degree of cure shall be confirmed by determining the glass transition temperature.

All pipe shall have an integral corrosion barrier of pure resin with a nominal cured thickness of 100 mils.

All pipe shall have a resin rich reinforced 10 mil nominal exterior layer with a UV (ultraviolet) inhibitor.

The pipe shall have a minimum design pressure of 150 psig @ 275°F following ASTM D2992 Procedure B.

Suggested specification for
Z-CORE® Piping System

Minimum Reinforced Wall Thickness:

1"	0.09inches
1½"-3"	0.14 inches
4"	0.17inches
6"	0.27 inches
8"	0.31 inches

3.02 Flanges and Fittings. All fittings shall be manufactured using the same type materials as the pipe. Fittings may be manufactured either by compression molding or filament winding/contact molding methods.

Fittings shall be adhesive bonded socket joint or flanged.

Flanges shall have ANSI B16.5 Class 150 bolt hole patterns.

3.03 Adhesive. Adhesive shall be manufacturer's standard for the piping system specified. All adhesive bonded joints shall be cured according to the manufacturers instructions for maximum structural strength and corrosion resistance.

3.04 Gaskets. Gaskets shall be 1/8" thick, 60-70 Durometer full-face type suitable for the service shown on the drawings and as recommended in the manufacturer's standard installation procedures.

3.05 Bolts, Nuts, and Washers. ASTM F593, 304 stainless steel hex head bolts shall be supplied. Two each SAE size washers shall be supplied on all nuts and bolts.

3.06 Acceptable Products. Z-CORE as manufactured by Smith Fibercast.

SECTION 4 – Installation and Testing

4.01 Training and Certification. All joints installed or constructed in the field shall be assembled by employees of the contractor who have been trained by the pipe manufacturer. The pipe manufacturer or their authorized representative shall train the contractor's employees in the proper joining and assembly procedures required for the project, including hands-on participation by the contractor's employees. Each bondor shall fabricate one pipe-to-pipe and one pipe-to-fitting joint that shall pass the minimum pressure test for the application as stated in section 2.04.d without leaking.

Only bondors who have successfully completed the pressure test shall bond pipe and fittings.

Certification by the Manufacturer shall be in compliance with ASME B31.3 Section A328.2.

4.02 Pipe Installation. Pipe shall be installed as specified and indicated on the drawings.

The piping system shall be installed in accordance with the manufacturer's current published installation procedures.

4.03 Testing. A hydrostatic pressure test shall be conducted on the completed piping system. The piping system shall be subjected to 1½ times the design operating pressure as stated in section 2.04.d. The pressure shall be held on the system for a minimum of one hour and the line inspected for leaks.

The test pressure should not exceed 1½ times the maximum rated operating pressure for the lowest rated element in the system.

The system shall be filled with water at the lowest point and air bled off from the highest point. Systems shall be brought up to test pressure slowly to prevent water hammer or overpressurization.

All pipe joints shall be water tight. All joints that are found to leak by observation or during testing shall be repaired by the contractor and retested.

This suggested specification is being provided only as a general reference for specifying FGS Smith Fibercast piping products. It is not intended to be all-inclusive or to address all of the specific applications or requirements for your particular project.

It is the policy of Fiber Glass Systems to improve its products continually. In accordance with that policy, the right is reserved to make changes in specifications, descriptions, and illustrative material contained in this bulletin as conditions warrant. Always cross-reference the bulletin date with the most current version listed at www.smithfibercast.com. The information contained herein is general in nature and is not intended to express any warranty of any type whatsoever, nor shall any be implied.

